

BLAST FURNACE – TAPHOLE CLAY

Products	Chemistry (%)					Density g/cm ³ (lb/ft ³)
	Al ₂ O ₃	SiO ₂	SiC	C	FeSi ₃ N ₄	
RSR 101	38.7 – 44.7	19.9 – 25.9	5.3-11.3	20-26	2-4	2.3-2.4 (145-149)
RSR 1170R-AM	30-34	32-36	10-12	20-24	2-4	2.2-2.2 (136-140)
RSR 1170-MODIFIED	29-35	23-29	7.3-13.3	24-30	2-8	2.2-2.2 (135 -139)
RSR 963-14	23-29	7-13	20.6-26.6	20.2-26.2	8.5-14.5	2.2-2.3 (140-146)
RSR GREEN TAP 5	35.5-41.5	8-14	16.5-22.5	23-28	2-4	2.3-2.4 (146-150)
RESTORATION CLAY	55-60	8-10	15-17	10-12	7-8	2.7-2.8 (168-172)

