

## Coreless Induction Furnace – Grout

### Copper Alloy

Products	Chemistry (%)		Density		Water Addition (%)	
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	g/cm <sup>3</sup>	lb/ft <sup>3</sup>	Vibration	Trowel
MINRO-AL® CAST A44	95.3	0.6	2.72	170	10.0-11.0	9.0
GROUT 163ACF	91.0	3.1	2.51	160	-	16.0-18.0
GROUT 563A	86.1	4.8	2.72	170	-	13.0-14.0
GROUT 663A	87.6	4.4	2.72	170	-	13.0-14.0
COIL CAST 97A	96.6	0.2	3.03	189	8.5-9.4	-
MINRO-SIL® GROUT S15	15.9	70.9	2.24	140	-	15.0-16.5