

## ROTARY HEARTH – BURNER BLOCKS

Products	Chemistry (%)		Density (g/cm <sup>3</sup> / lb/ft <sup>3</sup> )	Water Addition (%)	Temp. Limit
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>			
LCF 798A	61.5	35.0	2.64 / 165	5.4 - 5.9	1705°C / 3100°F
ALAKAST® 85 ULC	85.7	9.27	2.81 / 175.6	5.0 – 6.0	1705°C / 3100°F
KAST TECH 60	55.9	36.6	2.34 / 146	8.0 - 8.5	1705°C / 3100°F

