

Coreless Induction Furnace - Cover

Iron Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
INSULMIX® 33100	94.5	0.4	1.60	100	1815	3300
KAST TECH F80	50.9	41.1	2.24	140	1650	3000
QUICK CAST® 62	68.4	26.0	2.53	158	1705	3100