

PUSHER FURNACE – FLOOR

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)	Water Addition	Temperature Limit
	Al ₂ O ₃	SiO ₂			
BLAST KAST® 45 LC	45.3	49.3	2.14 / 134	7.0 – 8.0	1540°C / 2800°F

