

ROTARY HEARTH – BURNER BLOCKS

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)	Water Addition (%)	Temp. Limit
	Al ₂ O ₃	SiO ₂			
LCF 798A	61.5	35.0	2.64 / 165	5.4 - 5.9	1705°C / 3100°F
ALAKAST® 85 ULC	85.7	9.27	2.81 / 175.6	5.0 – 6.0	1705°C / 3100°F
KAST TECH 60	55.9	36.6	2.34 / 146	8.0 - 8.5	1705°C / 3100°F

