

ROTARY HEARTH – CURBS

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)		Water Addition (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	Vibration	Pump	Vibration	Pump	
TUFF-FLO 50	50.2	44.4	2.32 / 145	2.27 / 142	5.0 - 6.0	5.8 - 6.6	1650°C / 3000°F
ALAKAST® 50 LC-P	53.1	42.0	2.39 / 150		5.2 - 6.2		1650°C / 3000°F
ALAKAST® 68 LC-P	68.5	26.9	2.61 / 163		4.8 – 5.8		1650°C / 3000°F

