

## Channel Induction Furnace – Receiver/Pour Spouts

### Iron Alloy

Products	Chemistry (%)				Density		Temperature Limit	
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	SiC+C	Cr <sub>2</sub> O <sub>3</sub>	g/cm <sup>3</sup>	lb/ft <sup>3</sup>	°C	°F
CW 965 CASTABLE	69.0	28.0	-	-	2.65	165	1705	3100
CAST MAX MB HP	70.6	23.9	-	-	2.65	165	1790	3250
METAL KAST 85	81.2	11.7	-	-	2.85	178	1760	3200