

## Coreless Induction Furnace – Spout Copper Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	g/cm <sup>3</sup>	lb/ft <sup>3</sup>	°C	°F
RAM MAX® 70 P FINE	87.6	3.6	2.55	159	1650	3000
RAM MAX® 85 P	83.8	9.0	2.92	182	1760	3200
PRECAST SHAPES	45.0-90.0	-	-	-	1705	3100