

Coreless Induction Furnace - Spout Steel Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
RAM MAX® 85 P FINE	81.9	11.1	2.82	176	1760	3200
RAM MAX® 85 P	83.8	9.0	2.92	182	1760	3200
STEEL-PAK 90CR	73.1	12.3	2.93	183	1760	3200
PRECAST SHAPES	45.0-90.0	-	-	-	1705	3100