

Ladles – Working Lining Steel Alloy

Products	Chemistry (%)		Density		Water Addition (%)	Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³		°C	°F
CASTMAX® MB HP	70.6	23.9	2.61 – 2.68	163 – 167	4.0-5.0	1790	3250
DURACON® 32	64.5	29.8	2.54	158	4.0-5.5	1760	3200
DRI-VIBE® 916A	65.6	28.1	2.34	146	-	1650	3000
METAL KAST 85	82.6	12.4	2.85	178	4.7-5.7	1760	3200
METAL KAST 85C	83.8	9.7	2.85	178	5.0-6.0	1760	3200