

ROTARY HEARTH – SKID BLOCKS

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)	Water Addition (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂		Internal Vibration	External Vibration	
ULTRACON 34C	92.8	6.2	3.03 / 189	4.2 - 4.8	3.9 - 4.6	1760°C / 3200°F
ALPHAMAX® T						
ALAKAST™ 98 EZC	98.04	0.07	3.11 / 195	3.9 - 4.3		1705°C / 3100°F

