

CASTHOUSE TROUGH / RUNNER – SAFETY LINING

Products	Chemistry (%)				Density (g/cm ³ / lb/ft ³)	Water Addition (%)	Temp. Limit
	Al ₂ O ₃	SiC	SiC+C	SiO ₂			
DRI-VIBE® 660A	81.0	-	14.7	1.4	2.96 / 185	-	1650°C / 3000°F
RAM 491A	72.0	16.1	-	6.5	2.79 / 174	-	1760°C / 3200°F
CW 7929 CASTABLE	69.8	-	-	24.6	2.53 - 2.61 / 158 -163	4.5 - 5.5	1705°C / 3100°F

Products	Chemistry (%)			Density (g/cm ³ / lb/ft ³)	Temp. Limit
	Al ₂ O ₃	SiC+C	SiO ₂		
MATRIPUMP 80	81.0	-	12.7	2.82 / 176	
TEK-PAK 664A	67.3	13.7	9.3	2.89 / 175	1650°C (3000°F)

