

Channel Induction Furnace – Inductor Iron Alloy

Products	Chemistry (%)			Density		Temperature Limit	
	Al ₂ O ₃	MgO	SiO ₂	g/cm ³	lb/ft ³	°C	°F
DRI-VIBE® 306A	92.0	6.6	0.8	3.04	190	1785	3250
MINRO-MAG® RAM M10	6.7	88.6	1.5	2.83	177	1785	3250
DRI-VIBE® 696M	11.0	84.0	1.6	2.83	177	1785	3250