

## PUSHER FURNACE – SIDE WALLS

Products	Chemistry (%)		Density (g/cm <sup>3</sup> / lb/ft <sup>3</sup> )		Water Addition (%)		Temp. Limit
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Vibration	Pump	Vibration	Pump	
BLAST KAST® 70 LC	65.3	29.0	2.36 / 148		7.5 - 8.5		1650°C / 3000°F
BLAST KAST® 45 LC	45.3	49.3	2.14 / 134		7.0 - 8.0		1540°C / 2800°F

