

PUSHER FURNACE – SUBHEARTH

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)	Water Addition (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂		Vibration	Pumped	
ALAKAST® 50 LC-P	53.1	42.0	2.39 / 150	5.2 - 6.2		1650°C / 3000°F
SUPER FIRETEMP X	-	-	0.64 / 40	4.0		930°C / 1700°F
TUFFCRETE® 2800	43.4	49.1	2.27 / 142	5.4 – 6.2	6.0 – 7.5	1540°C / 2800°F

