

Ladles – Patching & Maintenance

Aluminum Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
QUICK-FIRE® PATCH B	79.2	10.0	2.53	158	1650	3000
QUICK-FIRE® PATCH M	63.4	26.5	2.33	145	1650	3000
CW 608 SEAL	84.0	10.5	2.32-2.40	145-150	1760	3200
PLASTER 55AC	51.6	37.3	2.21	138	1640	3000