

Coreless Induction Furnace – Spout Iron Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
RAM MAX® 70 P FINE	67.8	26.6	2.69	168	1650	3000
RAM MAX® BR 70 P BLUE	66.3	26.8	2.56-2.63	160-164	1760	3200
PRECAST SHAPES	45.0-90.0	-	-	-	1705	3100