

Coreless Induction Furnace – Working Lining Aluminum Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
DRI-VIBE® 520A	90.7	4.5	3.04	190	1204	2200
DRI-VIBE® 558A-FR	90.7	4.5	3.04	190	1095	2000
DRI-VIBE® 622A	80.3	8.3	2.88	180	1425	2600
PRECAST CRUCIBLE/X-ACT	45-90	-	-	-	-	-