

Coreless Induction Furnace – Working Lining Steel Alloy

Products	Chemistry (%)			Density		Temperature Limit	
	Al ₂ O ₃	MgO	SiO ₂	g/cm ³	lb/ft ³	°C	°F
DRI-VIBE® 682A	84.1	15.0	0.2	3.14	196	1815	3300
DRI-VIBE® 883A	88.2	11.1	0.1	3.12	195	1815	3300
DRI-VIBE® 924A	89.7	10.1	0.2	3.01	188	1815	3300
DRI-VIBE® 936A	90.7	9.1	0.2	3.09	193	1815	3300
DRI-VIBE® 967CR	80.5	14.2	0.1	3.03	189	1815	3300
DRI-VIBE® 975A	87.0	12.2	0.2	3.12	195	1815	3300
DRI-VIBE® 985A	87.0	12.2	0.2	3.12	195	1815	3300
MINRO-MAG® RAM M20	-	98.5	0.5	2.88	180	1815	3300