



# ARMORMAX<sup>®</sup> 70 SR

VIBRATION CAST

## General Information

ARMORMAX<sup>®</sup> 70 SR is a 70% alumina, mullite-based, low-cement castable refractory with a high stainless steel fiber content to improve overall fracture toughness and thermal shock resistance. The enhanced flow of the refractory base mix allows this product to be mixed in most field mixers. It is particularly suitable for applications where high mechanical abuse and thermal cycling are encountered. The metal fibers used provide the optimum resistance to high temperature oxidation with continuous operation to 1200°C (2200°F) and intermittent operation to 1400°C (2600°F). The base refractory mix without the fibers is suitable for temperatures to 1700°C (3100°F).

## Chemical Analysis

Al <sub>2</sub> O <sub>3</sub>	70.1%
SiO <sub>2</sub>	25.5%
CaO	2.1%
TiO <sub>2</sub>	1.1%
Fe <sub>2</sub> O <sub>3</sub>	0.6%
Alkalies	0.3%
Other	0.3%

Maximum Use Temperature	1430°C (2600°F)
Material Required Vibration Cast	2.66 g/cm <sup>3</sup> (166 lb/ft <sup>3</sup> )
Grain Size	2 mm (8 mesh) and finer
Installation Method	Vibration Cast
Standard Packaging	25 kg (55 lb) multi-wall paper bags

## VIBRATION CAST DATA

Temperature		Density		PLC <sup>†</sup>	MOR		CCS		Porosity	Abrasion Resistance
°C	°F	g/cm <sup>3</sup>	lb/ft <sup>3</sup>	%	MPa	psi	MPa	psi	%	cm <sup>3</sup>
110	230	2.74	171.0	-	22.1	3200	77.2	11,200	12	-
815	1500	2.66	166.0	-0.2	27.6	4000	117.2	17,000	17	6.0
1093	2000	2.69	168.0	-0.4	24.8	3600	135.1	20,000	18	3.5
1400	2550	2.68	167.0	-0.2	23.4	3400	132.2	19,900	17	-

† Permanent Linear Change After Firing

## SET TIMES AND WATER REQUIREMENTS

	Vibration Cast
Water Required	4.5 - 6.5%
Working Time	1 - 3 hours
Initial Set	2 - 6 hours
Final Set	5 - 12 hours

## THERMAL SHOCK DATA

	2200°F Prefired and Shock Temperature (5 Cycles)
Unshocked CMOR, psi	3524
Shocked CMOR, psi	3550
Strength Retained, %	101

Allied Mineral Products, Inc. supplies a complete line of monolithic refractories for industrial applications. For more information or a complete evaluation of your refractory requirements, please contact your local Allied representative.

Warning: Contains aluminum oxide, aluminosilicates, cement, and silica. The International Agency for Research on Cancer (IARC) has classified crystalline silica inhaled in the form of quartz or cristobalite carcinogenic to humans. Refer to Material Safety Data Sheet for additional information and disposal instructions. Avoid breathing dust. Wear NIOSH approved respirator during installation, removal, and disposal of product to prevent inhalation of dust. Avoid contact with skin and eyes. Cement powder or freshly mixed castable may cause eye and skin irritation. Steam spalling, which can lead to personal injury, may result from improper drying and firing procedures. In case of eye contact, flush immediately and repeatedly with water and consult a physician. For safest use and optimum performance, proper practices must be followed.

(ARNMAX70SR)

Revised 9/16/13

© 2013 Allied Mineral Products, Inc.

THE INFORMATION STATED IS BASED ON THE BEST LABORATORY AND LITERATURE DATA AND IS NOT A WARRANTY OR A GUARANTEE, NOR A VIOLATION OF ANY PATENT. IT IS PRESENTED FOR CONSIDERATION AND VERIFICATION ONLY, AND IS NOT TO BE USED FOR SPECIFICATION PURPOSES.