

ROTARY HEARTH – HEARTH

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)	Water Addition (%)			Temp. Limit
	Al ₂ O ₃	SiO ₂		Vibration	Pump	Self-flow	
TUFF-FLO 60A	59.6	36.2	2.58 / 161	4.0 – 5.0	5.75 – 6.75	6.0 – 7.0	1700°C / 3100°F
ALAKAST® 50 LC-P	53.1	42.0	2.39 / 150	5.2 - 6.2			1650°C / 3000°F
ALAKAST® 68 LC-P	68.5	26.9	2.61 / 163	4.8 - 5.8			1650°C / 3000°F
ALAKAST® 90 LC-P	90.2	7.78	2.90 / 182	4.3 - 4.8			1760°C / 3200°F

