

ROTARY HEARTH – SUBHEARTH

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)		Water Addition (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	Vibration	Pump	Vibration	Pump	
ALAKAST® 50 LC-P	52.4	42.8	2.39 / 149.5		5.2 – 6.2		1650°C (3000°F)
TUFFCRETE® 2800	43.4	49.1	2.27 / 142	2.18/136	5.4 – 6.2	6.0 –7.5	1540°C (2800°F)

