

Ladles – Back-up Lining

Copper Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
DRI-LITE 79AL-M	42.9	49.1	1.31	82	1370	2500