

## Ladles – Back-up Lining Aluminum Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	g/cm <sup>3</sup>	lb/ft <sup>3</sup>	°C	°F
DRI-LITE 79AL-M	42.9	49.1	1.31	82	1370	2500