

## Ladles – Coatings

### Steel Alloy

Products	Chemistry (%)			Density		Water Addition (%)	Temperature Limit	
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	MgO	g/cm <sup>3</sup>	lb/ft <sup>3</sup>	Trowel	°C	°F
T-COAT® 689M	3.5	8.5	83.0	2.05	128	20.0-22.0	1705	3100
T-COAT® 692M	-	-	56.0	2.0	125	18.0-20.0	1650	3000
CW 85 KOTE	2.9	9.5	82.2	1.54-1.70	96-106	20.0-30.0	-	-
LADLE WELL SPRAY	11.8	80.6	-	1.75	109	-	1540	2800