

Ladles – Coatings

Zinc Alloy

Products	Chemistry (%)			Density		Water Addition (%)	Temperature Limit	
	Al ₂ O ₃	SiO ₂	ZrO ₂	g/cm ³	lb/ft ³		°C	°F
MATRIKOTE 90AC	90.4	1.5	-	2.88	180	-	1650	3000
MINRO-Z WASH Z77	1.2	35.4	55.0	-	-	15.0-25.0	1650	3000