

Channel Induction Furnace - Cover

Zinc Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
KAST TECH F80	50.9	41.1	2.24	140	1650	3000