

Ladles – Working Lining

Zinc Alloy

Products	Chemistry (%)		Density		Water Addition (%)		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	Vibration	Pump/Pour	°C	°F
MATRIFIRE® 8085 ACX	78.6	8.8	2.79	174	5.9-6.4	6.4-7.4	1315	2400
QUICK-FIRE® 88	88.6	3.5	2.84	177	-	-	1650	3000
MATRIFLO Zn	66.8	26.7	2.56	160	5.1-5.5	-	1260	2300