

Pusher Furnace

Application Guide


HIGHLIGHTS

- A complete range of pumpable (ALAKAST) and shotcrete (BLAST KAST) castable products
- Wide selection of Precast Refractory Shapes available

ALLIED BENEFITS

- Global sales, service, and engineering teams
- Flexible worldwide manufacturing and supplier capabilities
- State of the art research capabilities





Ceramic Skid Blocks



Ceramic Starter Blocks



alliedmineral.com

Area	Products	Туре	Percentage	Installation Method
Extractor	ALAKAST [®] 85 LC-P-ES	Alumina	87.5	Pump
Shapes	ALAKAST [®] 90 LC-P	Tabular Alumina	90.2	Pump
Area	Products	Туре	Percentage	Installation Method
Hearth	ALAKAST [®] 85 LC-P-ES	Fused Alumina	87.5	Pump
	ALAKAST [®] 90 LC-P	Tabular Alumina	90.2	Pump
	TUFF-FLO 98	Tabular Alumina	98.6	Vibration, Shotcrete, Pump
Area	Products	Туре	Percentage	Installation Method
Subhearth	ALAKAST [®] 50 LC-P	Alumina / Silica	52.4 / 42.8	Vibration, Pump
	TUFFCRETE [®] 2800	Silica / Alumina	48.9 / 43.6	Vibration, Pump , Shotcrete
Area	Products	Туре	Percentage	Installation Method
BUMPER &	ALAKAST [®] 98 EZC	Alumina	98.0	Vibration
SKID BLOCKS	ULTRACON 34C	Tabular Alumina	92.8	Vibration
Area	Products	Туре	Percentage	Installation Method
Leading edge	ALAKAST [®] 90 LC-P	Tabular Alumina	90.2	Pump
	TUFF-FLO 98	Tabular Alumina	98.6	Vibration, Shotcrete, Pump
Area	Products	Туре	Percentage	Installation Method
Burner Walls & Roof	BLAST KAST [®] 70 LC	Mullite	65.3	Shotcrete
	ALAKAST [®] 65-LC-P	Alumina	64.7	Vibration, Pump
Area	Products	Туре	Percentage	Installation Method
SIDE WALLS	BLAST KAST [®] 70 LC	Mullite	65.3	Shotcrete
	BLAST KAST [®] 45 LC	Alumina / Silica	45.3 / 49.3	Shotcrete
Area	Products	Туре	Percentage	Installation Method
WET SKID	ALAKAST 68 [®] LC-P	Alumina	68.5	Pump
System	TUFF-FLO 65M	Mullite	64.3	Vibration, Pump
Area	Products	Туре	Percentage	Installation Method
Floor	BLAST KAST [®] 45 LC	Alumina / Silica	45.3 / 49.3	Shotcrete