

Coreless Induction Furnace – Spout

Iron Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
MINRO-AL® PLASTIC A76	67.3	25.7	2.69	168	1650	3000
RAM MAX BR 70-P	69.9	23.4	2.56-2.63	160-164	1760	3200
PRECAST SHAPES	45.0-90.0	-	-	-	1705	3100