

MORTARS for FOUNDRY

AIRSET

Products	Chemistry (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	
BRIKSET® 30 TC	28.5	67.2	1650°C (3000°F)
BRIKSET® 30 DC	29.7	65.5	1650°C (3000°F)
BRIKSET® 40 TC	40.0	56.0	1650°C (3000°F)
BRIKSET® 40 DC	39.9	54.1	1650°C (3000°F)
BRIKSET® 40 STC	40.2	52.5	1650°C (3000°F)
BRIKSET® 65 TC	65.5	29.0	1785°C (3250°F)
BRIKSET® 65 DC	65.5	29.0	1785°C (3250°F)
BRIKSET® 711	67.1	28.0	1705°C (3100°F)

HEAT SET

Products	Chemistry (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	
ARMORSET 80 P	77.8	10.3	1760°C (3200°F)
ARMORSET 90 P	88.1	2.9	1815°C (3300°F)
ARMORSET 75 15SIC P	73.3	3.8	1705°C (3100°F)

