

DRY VIBRATABLES for STEEL

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)	Temp. Limit
	Al ₂ O ₃	SiO ₂		
DRI-VIBE® 660A	81.0	1.4	2.96 / 185	1650°C (3000°F)
LADLE-VIBE® 50	51.0	43.8	2.16 / 135	1760°C (3200°F)
LADLE-VIBE® 60	55.3	41.3	2.16 / 135	1760°C (3200°F)
LADLE-VIBE® 60 NO BOND	55.9	38.7	2.16 / 135	1760°C (3200°F)
LADLE-VIBE® 82	79.0	14.7	2.51 / 157	1760°C (3200°F)
LADLE-VIBE® 88 NO BOND	84.0	8.6	2.64 / 165	1760°C (3200°F)
LADLE-VIBE® 90M				1760°C (3200°F)
DRI-VIBE® 660A	81.0	1.4	2.96 / 185	1650°C (3000°F)
LADLE-VIBE® 50	51.0	43.8	2.16 / 135	1760°C (3200°F)
LADLE-VIBE® 60	55.3	41.3	2.16 / 135	1760°C (3200°F)

