

MORTARS for HEAT TREATING & FORGING

Products	Chemistry (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	
BRIKSET 30 TC	28.5	67.2	1650°C (3000°F)
BRIKSET 30 DC	29.7	65.5	1650°C (3000°F)
BRIKSET 40 TC	40.0	56.0	1650°C (3000°F)
BRIKSET 40 DC	39.9	54.1	1650°C (3000°F)
BRIKSET 40 STC	40.2	52.5	1650°C (3000°F)
BRIKSET 65 TC	65.5	29.0	1788°C (3250°F)
BRIKSET 65 DC	65.5	29.0	1788°C (3250°F)
DURAL 81P MORTAR	76.7	10.6	1760°C (3200°F)
DURATAB MORTAR	88.0	2.9	1815°C (3300°F)
DURATAB C MORTAR	79.3	2.9	1815°C (3300°F)
DURATAB SC MORTAR	73.4	3.6	1705°C (3100°F)
BRIKSET 711	67.1	28.0	1705°C (3100°F)

