

Channel Induction Furnace - Cover

Copper Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
QUICK CAST® 62	68.4	26.0	2.53	158	1705	3100
KAST TECH F80	50.9	41.1	2.24	140	1650	3000