

## Channel Induction Furnace - Cover Iron Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	g/cm <sup>3</sup>	lb/ft <sup>3</sup>	°C	°F
INSULMIX® 33100	94.5	0.4	1.60	100	1815	3300
QUICK CAST® 62	68.4	26.0	2.53	158	1705	3100
KAST TECH F80	50.9	41.1	2.24	140	1650	3000