

## Box Furnace (Forge) – Curb Walls

Products	Chemistry (%)		Density		Water Addition (%)		Temperature Limit	
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	g/cm <sup>3</sup>	lb/ft <sup>3</sup>	Vibration	Pumped	°C	°F
TUFF-FLO 50	50.2	44.4	2.32 (V) 2.27 (P)	145 (V) 142 (P)	5.0-6.0	5.8-6.6	1650	3000
RAM MAX® 45 AS	42.2	52.7	2.24-2.33	140-146	-	-	1649	3000

V = Vibration

P = Pumped