

## MORTARS for FOUNDRY

### AIRSET

Products	Chemistry (%)		Temp. Limit
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	
BRIKSET 30 TC	28.5	67.2	1650°C (3000°F)
BRIKSET 30 DC	29.7	65.5	1650°C (3000°F)
BRIKSET 40 TC	40.0	56.0	1650°C (3000°F)
BRIKSET 40 DC	39.9	54.1	1650°C (3000°F)
BRIKSET 40 STC	40.2	52.5	1650°C (3000°F)
BRIKSET 65 TC	65.5	29.0	1785°C (3250°F)
BRIKSET 65 DC	65.5	29.0	1785°C (3250°F)
BRIKSET 711	67.1	28.0	1705°C (3100°F)

### HEAT SET

Products	Chemistry (%)		Temp. Limit
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	
ARMORSET 80 P	77.8	10.3	1760°C (3200°F)
ARMORSET 90 P	88.1	2.9	1815°C (3300°F)
ARMORSET 75 15SIC P	73.3	3.8	1705°C (3100°F)

