

Channel Induction Furnace – Inductor Zinc Alloy

Products	Chemistry (%)			Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	MgO	g/cm ³	lb/ft ³	°C	°F
QUICK-FIRE® ONE 86	87.6	3.6	-	2.55	159	1650	3000
DRI-VIBE® 558A-FR	90.7	4.5	-	3.04	190	1095	2000
CERALOOP	-	-	-	-	-	-	-