

Coreless Induction Furnace – Spout Zinc Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
QUICK-FIRE® ONE 86	87.6	3.6	2.55	159	1650	3000
QUICK-FIRE® 88	88.6	3.5	2.84	177	1650	3000
RAM MAX® 70 P FINE	67.8	26.6	2.69	168	1650	3000
RAM MAX® 90 P FINE	88.4	6.9	2.88	180	1760	3200
PRECAST SHAPES	45.0-90.0	-	-	-	1705	3100