

Car Bottom Furnace (Heat Treat) Subhearth

Products	Chemistry (%)		Density		Water Addition (%)	Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	Vibration	°C	°F
INSULMIX® 2460 LI	44.8	34.9	1.0	62	-	1315	2400
INSULMIX® 2690 LI	46.3	42.5	1.52 (G) 1.44 (V)	95 (G) 90 (V)	-	1425	2600

V = Vibration

G = Gunning