

WALKING BEAM – FLOOR

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)		Water Addition (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	Vibration	Pump	Vibration	Pump	
BLAST KAST® 45 LC	45.3	49.3	2.14 / 134		7.0 - 8.0		1540°C / 2800°F

