

## WALKING BEAM – WET SKID SYSTEM

Products	Chemistry (%)		Density (g/cm <sup>3</sup> / lb/ft <sup>3</sup> )		Water Addition (%)		Temp. Limit
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	Vibration	Pump	Vibration	Pump	
TUFF-FLO 65M	64.3	31.2	2.58 / 161	2.50 / 156	4.25 - 5.75	5.5 - 6.5	1700°C / 3100°F
ALAKAST® 68 LC-P	68.5	26.9	2.61 / 163		4.8 - 5.8		1650°C / 3000°F

