

## WALKING BEAM – BURNER WALLS & ROOF

Products	Chemistry (%)		Density (g/cm <sup>3</sup> / lb/ft <sup>3</sup> )	Water Addition (%)	Temp. Limit
	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>			
BLAST KAST® 70 LC	65.3	29.0	2.36 / 148	7.5 - 8.5	1650°C / 3000°F
ALAKAST® 65 LC-P	64.7	30.7	2.40 / 150	6.5 - 7.5	1650°C / 3000°F

