

WALKING BEAM – HEAT ZONE SLOT & DEFLECTOR BLOCKS

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)		Water Addition (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	Vibration	Pump	Vibration	Pump	
TUFF-FLO 50	50.2	44.4	2.32 / 145	2.27 / 142	5.0 - 6.0	5.8 - 6.6	1650°C / 3000°F
TUFF-FLO 65M (Precast Shape)	64.3	31.2	2.58 / 161	2.50 / 156	4.25 - 5.75	5.5 - 6.5	1700°C / 3100°F
TUFFCRETE® 2800	43.4	49.1	2.27 / 142		5.4 - 6.2	6.0 - 7.5	1540°C / 2800°F

