

WALKING BEAM – WET SKID SYSTEM

Products	Chemistry (%)		Density (g/cm ³ / lb/ft ³)		Water Addition (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	Vibration	Pump	Vibration	Pump	
TUFF-FLO 65M	64.3	31.2	2.58 / 161	2.50 / 156	4.25 - 5.75	5.5 - 6.5	1700°C / 3100°F
ALAFLOW 60 LC-P	61.4	34.6	2.51 / 157		5.0 - 6.0		1650°C / 3000°F
ALAKAST™ 68 LC-P	68.5	26.9	2.61 / 163		4.8 - 5.8		1650°C / 3000°F

