

Channel Induction Furnace – Working Lining Zinc Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
MATRIFLO ZN	66.8	26.7	2.56	160	1260	2300
QUICK CAST® 62AC	65.0	29.5	2.72	170	1705	3100
PRECAST SHAPES	60.0-90.0	-	-	-	1705	3100
SUPER DUTY FIREBRICK	44.0	49.0	2.24	140	1600	2910