

MORTARS for HEAT TREAT & FORGE

Products	Chemistry (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	
BRIKSET® 30 TC	28.5	67.2	1650°C (3000°F)
BRIKSET® 30 DC	29.7	65.5	1650°C (3000°F)
BRIKSET® 40 DRY	42.6	50.9	1650°C (3000°F)
BRIKSET® 40 TC/DC	39.9	54.1	1650°C (3000°F)
BRIKSET® 40 STC	40.2	52.5	1650°C (3000°F)
BRIKSET® 65 TC/DC	65.5	29.0	1790°C (3250°F)
BRIKSET® 65 DRY	66.8	25.9	1700°C (3100°F)
ARMORSET 80 P	77.8	10.3	1760°C (3200°F)
ARMORSET 90 P	88.1	2.9	1815°C (3300°F)
ARMORSET 85 10CR P	84.5	0.6	1760°C (3200°F)
ARMORSET 75 15SIC P	73.3	3.8	1700°C (3100°F)

