

Reverberatory Furnace – Hearth

Aluminum Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
MATRIPUMP 63 ACX	64.2	27.5	2.59	162	1540	2800
MATRIPUMP 70 ACX	73.4	20.3	2.74	171	1482	2700
MATRIPUMP 72 ACX	78.6	15.6	2.68	167	1540	2800
MATRIFLO 80 ACX PUMP	78.0	13.9	2.64	165	1540	2800
MATRIFLO 85 ACX	85.6	8.5	2.74	171	1540	2800
NANO-TEK® 60 AL HS	62.3	31.6	2.45	153	1500	2730