

Reverberatory Furnace – Roof

Aluminum Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
KAST TECH 30	56.0	36.5	2.44	146	1700	3100
MATRIPUMP AR 61	60.8	34.2	2.46 (V) 2.50 (P)	154 (V) 156 (P)	1650	3000
MATRIPUMP 50	53.9	40.3	2.47	154	1650	3000
NANO-TEK® 65 HS	60.7	35.1	2.52	157	1705	3100
NANO-TEK® 70	68.1	28.6	2.50	156	1705	3100